

Bitumen 60/70

No.	Test	Test / Metod	Bitumen	Grade 60-70	
		ISIRI	Result	Min	Max
1	Softening point °C	12505	48	46	-
2	Flash point °C		+300	230	-
3	Penetration @ 25 °C, 10 ⁻¹ mm		66	60	70
4	Solubility in trichloroethylene, wt%		99.8	99.00	-
5	Ductility @ 25 °C, Cm		+100	100	-
6	Thin-Film Oven Test				
6-1	Change in Mass, wt%		0.1	-	0.8
6-2	Retained Penetration @ 25 °C, % of original		74	52	-
6-3	Ductility of Residue @ 25 °C, Cm		+100	50	-

Site Manager

Laboratory Manager

